




Essence

Specification according to EN 1307

Type of manufacture	ISO 2424	Tufted 1/10 "						
Aspect	ISO 2424	Loop pile						
Dye method	Solution dyed							
Dimension	EN ISO 24342	cm x cm	50 x 50 / 19,68" x 19,68"			(20 tiles per box)		
Primary backing	ISO 2424	Polyester fleece						
Secondary backing	ISO 2424	ProBase - modified bitumen.						
Pile fibre composition	ISO 2424	BCF Polyamide 6						
Total thickness	ISO 1765	mm	5.5	inch	0.2			
Effective pile thickness	ISO 1766	mm	2.6	inch	0.10			
Total mass	ISO 8543	g/m ²	3900	oz/yd ²	115.1			
Total pile mass	ISO 2424	g/m ²	500	oz/yd ²	14.8			
Effective pile mass	ISO 8543	g/m ²	310	oz/yd ²	9.1			
Pile density	ISO 8543	g/cm ³	0.119	lb/in ³	0.0043			
Number of tufts	ISO 1763	/dm ²	1580	/yd ²	132104			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307	33 Commercial - heavy use						
Luxury rating	EN 1307	LC 1						
Dimensional stability	EN 986	%	≤ 0,20					
Impact sound reduction ΔL _w	ISO 10140	dB	24					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.01	0.01	0.05	0.17	0.29	0.31
Noise reduction	ISO 354	α _w	0.15					
Thermal resistance	ISO 8302	m ² .K/W	0.040					
Flammability	EN 13501-1	Bfl - s1 (loose laid tested)						
Prodis - GUT	www.pro-dis.info	835EB08F						


 Manufactured by:
 Tarkett BV
 Taxandriaweg 15
 NL - 5142 PA Waalwijk
 EN 14041
 0493-CPR-0002

This specification sheet is also valid for all colours of product "Essence 530".









DESSO flooring products are to be installed in full accordance with Tarkett's installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. DESSO flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com